




- (51) **International Patent Classification⁷:** C22B 11/06, 1/08
 (21) **International Application Number:** PCT/CA2004/001067
 (22) **International Filing Date:** 20 July 2004 (20.07.2004)
 (25) **Filing Language:** English
 (26) **Publication Language:** English
 (30) **Priority Data:**
 2,435,779 22 July 2003 (22.07.2003) CA
 60/489,904 25 July 2003 (25.07.2003) US
 (71) **Applicant (for all designated States except US):** RESSOURCES MINIERES PRO-OR INC. [CA/CA]; 400 Rue St-Jacques, Suite 200, Montreal, Quebec H2Y 1S1 (CA).
 (72) **Inventors; and**
 (75) **Inventors/Applicants (for US only):** BERGERON, Mario [CA/CA]; 1253 de Fenouillet, Cap-Rouge, Quebec G1Y 2Y6 (CA). RICHER-LAFLECHE, Marc [CA/CA]; 1303 Rue De Chambly, Sainte-Foy, Quebec G1W 3Y8 (CA).
 (74) **Agents:** DUBUC, J. et al.; Goudreau Gage Dubuc, Stock Exchange Tower, 800 Place Victoria, Suite 3400, P.O. Box 242, Montreal, Quebec, H4Z 1H9 (CA).
 (81) **Designated States (unless otherwise indicated, for every kind of national protection available):** AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GI, GM, GR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
 (84) **Designated States (unless otherwise indicated, for every kind of regional protection available):** ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

- (54) Title:** A PROCESS FOR RECOVERING PLATINUM GROUP METALS FROM ORES AND CONCENTRATES



- (57) Abstract:** A method for recovering at least one platinum group metal (PGM) species from a feed product selected from the group consisting of chromite ore, chromite ore concentrate and PGM concentrate comprising the steps of : mixing the feed with at least one salt so as to produce a mixture, whereby the concentration of salt in the mixture is sufficient to convert at least one PGM species into a corresponding PGM chloride salt; and contacting the mixture with gaseous chlorine and CO at a temperature between about 240°C and 800°C to induce the conversion of at least one species of PGM into a corresponding PGM chloride salt, whereby said chloride salt of at least one PGM species can be recovered.

- with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.